

O.D. (in.) (mm)	Weight With Coupling Lbs/Ft	Wall Thickness (in.) (mm)	I.D. (in.) (mm)	Drift Diameter (in.) (mm)	Coupling or Joint O.D.		Bored Pin I.D. (in.) (mm)	Grade	Collapse Resistance (PSI)**	Internal Yield Pressure (PSI)**			Body Yield Strength (1000 Lbs)**	Joint Yield Strength (1000 Lbs)**					
					Round or Buttress (in.) (mm)	Other (in.) (mm)				Plain End or Extreme Line	Round Thread			Buttress Thread	Threaded and Coupled Joint Round Thread		Other*		
											Short	Long			Short	Long			
4.5 114.3	9.50	.205 5.21	4.090 103.9	3.965 100.7	5.000 127.0	4.500 114.3	4.010 101.9 3.990 101.3	H-40	2760	3190	3190	-	-	111	77	-	-	-	
								J-55 K-55	3310	4380	4380	-	-	152	101 112	62	74	-	
4.5 114.3	10.50	.224 5.69	4.052 102.9	3.927 99.75	5.000 127.0	4.651 118.1 4.500 114.3 4.921 125.0 4.824 122.5 4.862 123.5	3.996 101.5 3.952 100.4 3.959 100.5 3.977 101.0	J-55 K-55	4010	4790	4790	-	-	165	132 146	69 80 129	143(22) 165(9a,9b, 30,31)	166(28) 176(23) 181(22)	
								J-55 K-55	4960	5350	5350	5350	5350	184	154 170	162 180	95 97 160 163	174(8) 184(9a,9b, 27,28,30,31)	203(22) 207(23)
4.5 114.3	11.60	.250 6.35	4.000 101.6	3.875 98.43	5.000 127.0	4.500 114.3 4.695 119.2 4.867 123.6 4.862 123.5 5.000 127.0 4.921 125.0 4.874 123.8	3.996 101.5 3.930 99.82 3.907 99.24 3.925 99.69	C-75	6100	7290	-	7290	7290	250	-	212	131	174(8)	250(9a,9b)
								L-80 N-80	6350	7780	-	7780	7780	267	-	212 223	131 141 190	214(22) 218(23)	267(9a,9b, 27,28,30,31)
								C-95	7030	9240	-	9240	9240	317	-	234	164 167	193(8) 224(22)	229(23) 317(9a,9b)
								P-110	7580	10690	-	10690	10690	367	-	279	190 194 229	267(22) 272(23)	367(9a,9b, 27,28,30,31)
								Q-115	15840	16380	-	16380	15300	551	-	438	216	220(25)	417(9a,9b)
4.5 114.3	12.60	.271 6.88	3.958 100.5	3.833 97.36	5.000 127.0	4.901 124.5 4.584 116.4 4.981 126.5 4.729 120.1 4.950 125.7 4.921 125.0 4.961 126.0 4.892 124.3	3.996 101.5 3.883 98.63 3.886 98.70	K-55	5720	5790	-	-	-	199	-	-	148	198	231 247
								C-75	7200	7900	-	-	-	271	-	-	171	188(8)	270(9a,9b)
								N-80	7500	8440	-	-	-	289	-	-	180 198	243(23) 260(21)	288
								C-95	8400	10010	-	-	-	343	-	-	188 208	255(23) 273(21)	342(9a,9b)
5.0 127.0	11.5	.220 5.59	4.560 115.8	4.435 112.6	5.563 141.3	5.000 127.0 5.500 139.7	4.460 113.3	J-55 K-55	3060	4240	4240	-	-	182	133 147	75	141(8)	-	
5.0 127.0	13.0	.253 6.43	4.494 114.1	4.369 111.0	5.563 141.3	5.364 136.2 5.563 141.3 5.587 141.9 5.375 136.5 5.511 140.0 5.000 127.0	4.494 114.1 4.421 112.3 4.419 112.2 4.468 113.5	J-55 K-55	4140	4870	4870	4870	4870	208	169 186	182 201	108 113 185	190(7) 197(8) 235(23)	209(9a,9b 28,30,31)
								C-75	4990	6640	-	-	-	283	-	-	-	-	-
								N-80	5140	7090	-	-	-	302	-	-	157 164	241 247	276 302
5.5 139.7	14.0	.244 6.20	5.012 127.7	4.887 124.1	6.050 153.7	5.660 143.8 6.050 153.7 5.500 139.7	4.937 125.4 4.912 124.6 4.941 125.5	H-40	2630	3110	3110	-	-	161	130	-	-	-	
								J-55 K-55	3120	4270	4270	-	-	222	172 189	-	92 118	172 195	247
								C-75	3560	5820	-	-	-	302	-	-	-	-	-
5.5 139.7	15.5	.275 6.98	4.950 125.7	4.825 122.6 4.653 118.2	6.050 153.7	5.713 145.1 5.500 139.7 6.050 153.7 6.043 153.5 5.900 149.8 6.000 152.4 5.860 148.8 5.862 148.9 6.051 153.7 6.075 154.4 5.905 150.0	4.890 124.2 4.875 123.8 4.746 120.5 4.950 125.7	J-55 K-55	4040	4810	4810	4810	4810	248	202 222	217 239	122 130 229	236 230	248 291
								C-75	4860	6560	-	-	-	339	-	-	339	-	-
								N-80	4990	7000	-	-	-	362	-	-	178 188	332	361
								P-110	5620	9620	-	-	-	497	-	-	497	-	-